

180 PE SERIES



Technical Data Sheet

Screen printing inks

1. APPLICATION FIELDS:

Versatile one and two component ink for screen printing on ABS, acrylic glass, lacquered surfaces, metal, paper, carton, polyamide, polycarbonate, pre-treated polyethylene (PE) and polypropylene (PP), polystyrene, polyurethane and rigid PVC.

Substrates may differ in their chemical structure or method of manufacture. A test for suitability must always be carried out before printing. Antistatic, Mould Release Agents and Slip Additives may have negative effects on adhesion, and should be detected and removed prior to printing.

2. CHARACTERISTICS:

This glossy, physically drying and chemical reactive screen printing ink exhibits good mechanical and chemical resistance, as well as a good flexibility. The colour shades of 180 PE are light fast, weather resistant and guarantee high opacity. A special product test is recommended prior to production.

The raw materials used meet with the limits stipulated by the EEC regulation EN 71 (Safety of Toys), part 3 (Migration of Certain Elements) of December 1994.

3. RANGE OF COLOURS:

The basic ink mixing system consists of 12 basic colours and may be used for the mixing of a wide colour shade range. Field proven mixing formulations exist for Pantone®, HKS, RAL, NCS, etc. (see 6.2).

3.1 Basic colours:

3.1.1. Standard ink series:

The basic colours of series B exhibit better light fastness as well as higher opacity than series G.

Light Yellow	B 1	180 PE 2423
Medium Yellow	B 2	180 PE 2424
Orange	B 3	180 PE 30115
Light Red	B 4	180 PE 30116
Red	B 5	180 PE 30117
Pink	B 6	180 PE 30118
Violet	B 7	180 PE 50027
Blue	B 8	180 PE 50028
Green	B 91	180 PE 60045
Brown	B 10	180 PE 8432
White	B 11	180 PE 1065
Black	B 12	180 PE 9028
Clear Base		180 PE 0016

3.1.2. Basic colours with less light fastness:

Light Yellow	G 1	180 PE 2170
Medium Yellow	G 2	180 PE 2414
Orange	G 3	180 PE 3452
Light Red	G 4	180 PE 30093
Red	G 55	180 PE 30634
Pink	G 6	180 PE 3455
Violet	G 7	180 PE 5434
Blue	G 8	180 PE 5435
Green	G 91	180 PE 60038
Brown	G 10	180 PE 8225
White	G 11	180 PE 1026
Black	G 12	180 PE 9005
Clear Base		180 PE 0016

3.2 Special Products:

3.2.1 High Opacity Formulations:

White	(high opacity)	180 PE 1031
-------	----------------	-------------

3.3 Euro-Colours / 4-Colour Process Printing Inks:

For 4-colour process printing according to DIN 16538, 4 Euro-basic colours are available:

Euro-Yellow	180 PE 2085
Euro-Magenta	180 PE 3240
Euro-Cyan	180 PE 5235
Halftone Black	180 PE 9045

3.4 Bronze Colours:

see separate "Bronze Colours" leaflet

4. ADDITIONAL PRODUCTS:

Raster paste can be added to reduce "Dot Gain" and to achieve sharper dots.

Raster Paste	(max. addition: 10 %)	180 PE 0013
--------------	-----------------------	-------------

5. ADDITIVES:

5.1 Thinner:

Prior to production, the screen printing ink has to be adjusted to the printing viscosity by the addition of thinner.

Thinner, very fast	(addition: 15 - 25 %)	VS 35 353
Thinner, standard	(addition: 15 - 25 %)	VD 38 571

180 PE SERIES

While printing on plastics such as ABS, acrylic glass and styrene, tension corrosion can appear while using certain solvents. In order to avoid such effect the special thinner 35 696 should be used.

Special Thinner (addition: 15 - 25 %) 35 696

5.2 Retarder

Retarder will influence the drying time of the ink under different climate conditions. Retarder VZ 35 928 is a medium drying retarder, VZ 34928 is a very slow drying retarder. While using the ink under extreme climate conditions (Temperature higher than 28°C) it is recommended to use the retarder VZ 35 928 as a thinner to adjust the viscosity of the ink.

Retarder, standard (addition 5 – 10 %) VZ 35 928
Retarder, slow (addition max. 5 %) VZ 34 392

It must be noted that an excessive addition of retarder may negatively influence the ink transfer and the bulk goods resistance, due to the slow evaporation of the retarder. Retarder VZ 34 392 should only be used in conjunction with thinner VD 38 571 or retarder VZ 35 928.

5.3 Hardener:

Hardener 37172 is the standard hardener. The mixing ratio is 10 parts of ink with 1 part of hardener. At room temperature of 20° C a pot life of approximately 12 hours can be achieved.

If a faster hardening of the ink is required, hardener SE 5214 is recommended. At room temperatures the pot life is approx. 8 hours.

Hardener, standard 37172
10 parts of ink, with 1 part of hardener
Hardener SE 5214
10 parts of ink with 1 part of hardener

Please note that the final chemical and physical resistance of the ink is only achieved after 36 hours at room temperature of 20° C.

During processing and drying of the printed ink, the temperature should not be lower than 15° C otherwise the chemical crosslinking is stopped. Also avoid high humidity for several hours after printing as the hardener is sensitive to humidity. While using hardener please note that multi-colour jobs have to be printed during 36 hours. The completely dried ink can not be overprinted.

5.4 Levelling Agent:

The levelling of the ink surface can be optimised by the use of a levelling agent. It must be noted that excessive addition of levelling agent can have a negative influence on the overprintability.

Levelling Agent (max. add.: 0,5-1 %) VM 100 VR 133

6. PROCESSING INSTRUCTIONS:

6.1 Pre-treatment:

Pre-treatment of polyolefines (PE/PP) must be performed by Flame Treatment or CORONA-discharge in order to insure the adhesion of the screen printing ink to the substrate. In case of PE, surface tension needs to be at least 42 mN/m (Dynes/cm), in case of PP at least 52 mN/m (Dynes/cm).

6.2 Stencils/Printing Equipment:

The inks of 180 PE series can be printed with all commonly available screen printing meshes. They can be used with all screen printing machines for printing speeds of about 1.800 – 3.600 pieces/h with screen printing stencils currently used for industrial applications. The colour mixing formulations are based on a 120-34 threads/cm mesh.

6.3 Curing Conditions:

The inks of 180 PE series are physically drying through the evaporation of solvent during 5 min. at 20° C and then are drying chemically by the addition of hardener. While multi-colour printing we recommend an intermediate drying process by infrared lamps or hot air blower. The finally drying will be achieved at 40 – 50 ° C during 1 – 2 minutes.

7. CLEANING:

Clichés, squeegees and so on can be cleaned with the RUCO Universal cleaner 32 335. It must be noted that the screen does not come into contact with solvents. For the cleaning of the screen please see to the application references of the screen manufacturers. If cleaning is not performed by fully automatic cleaning equipment, protective gloves must be worn.

Universal Cleaner UR 32 335
Cleaner for cleaning equipment WR 100 VR 1240C
Bio degradable Cleaner BR 100 VR 1272

180 PE SERIES

8. SHELF LIFE:

A shelf life of 12 months is guaranteed when storing the inks at 21°C and in the original packing container. At higher storage temperatures the shelf life will be reduced.

9. PRECAUTIONS:

For further information on the safety, storage and environmental aspects concerning these products, please refer to the Material Safety Data Sheet (MSDS).

Additional technical information may be obtained from our staff of the Technical Application Department.

A.M. RAMP & Co. GmbH
Lorsbacher Strasse 28
D-65817 Eppstein

Tel: ++49 (0) 6198-304-0 FAX: ++49 (0) 6198-304-287
E-Mail: info@ruco-inks.com



The above statements are accurate to our best knowledge and belief. However, due to the great number of possible influences during the manufacture of the substrate and the variation in the application process we suggest that suitability testing take place under actual conditions before production. No legally binding guarantee of certain properties or of the suitability for a definite application purpose can be derived from the above information.

ATM-180 PE-070730-3